

QUALITY DEPARTMENT

ISO 9001:2015

ISO 14001:2015

BS OHSAS 18001:2007

Q04.05.PPL23 Declaration of Conformity

Date of issue: March 2017

Valid until: March 2020



**BWC d.o.o Beograd**  
 Beogradska 129,  
 Belgrade, Serbia  
 T: + 381.11.8408.654  
 F: + 381.11.8408.659  
 E: office@bwc.rs  
 www.bwc-bg.com

ENGINEERING PLASTIC PRODUCTS  
 UHMWPE SHEETS

## Polyplate PE-1000 R

Based on Regenerated material UHMWPE and HDPE (milled or grinded)

PROPERTY	TEST METHOD	UNIT	VALUE
DENSITY	ISO 1183	kg/cm <sup>3</sup>	930-960
MELT FLOW RATE (190°C/21,6 kg)	ISO 1133	g/10 min	-
MOLECULAR WEIGHT	ISO 1133	g/mol x 10 <sup>6</sup> mol	>1,2
TENSILE STRENGTH AT YIELD ( 50 mm/min)	ISO 527-2/1A	MPa	-
TENSILE MODULUS (1h)	ISO 527	MPa	700
TENSILE CREEP MODULUS (1000h)	ISO 899-1	MPa	-
CHARPY IMPACT STRENGTH (14° V-NOTCH BOTH SIDES)	ISO 527	kJ/m <sup>2</sup>	130
SHORE D HARDNESS	ISO 868	Shore D	61
VICAT SOFTENING POINT (1 kg)	ISO 306	°C	121

The information in this data sheet represents typical values and should not be used as a specification.