

QUALITY DEPARTMENT
 ISO 9001:2015
 ISO 14001:2015
 ISO 45001:2018

Declaration of Conformity
Date of issue: March 2020
Valid until: February 2023



BWC d.o.o Beograd
 Beogradska 129,
 Belgrade, Serbia
 T: + 381.11.8408.654
 F: + 381.11.8408.659
 E: office@bwc.rs
 www.bwc-bg.com

ENGINEERING PLASTIC PRODUCTS
 UHMWPE SHEETS

Polyplate PE-1000 R

Based on Regenerated material UHMWPE and HDPE (milled or grinded)

PROPERTY	TEST METHOD	UNIT	VALUE
DENSITY	ISO 1183	kg/cm ³	930-960
MELT FLOW RATE (190°C/21,6 kg)	ISO 1133	g/10 min	-
MOLECULAR WEIGHT	ISO 1133	g/mol x 10 ⁶ mol	>1,2
TENSILE STRENGTH AT YIELD (50 mm/min)	ISO 527-2/1A	MPa	-
TENSILE MODULUS (1h)	ISO 527	MPa	700
TENSILE CREEP MODULUS (1000h)	ISO 899-1	MPa	-
CHARPY IMPACT STRENGTH (14° V-NOTCH BOTH SIDES)	ISO 527	kJ/m ²	130
SHORE D HARDNESS	ISO 868	Shore D	61
VICAT SOFTENING POINT (1 kg)	ISO 306	°C	121

The information in this data sheet represents typical values and should not be used as a specification.